

U.S. Serial No. 10/597,169  
Response dated: July 8, 2011  
Response to Office Action dated: June 8, 2011

### **SPECIFICATION AMENDMENT**

Please amend the specification as follows:

At page 14, please amend the last paragraph as follows:

Preferably, the coatings made of the inventive composition ~~has~~ have a low water vapor transmission rate (WVTR). The WVTR may be less than 15.5 g/m<sup>2</sup>/24h for a coating weight of 20 g/m<sup>2</sup>. Hence, it is preferred that the WVTR is lower than 15.4 g/m<sup>2</sup>/24h, more preferably lower than 15 g/m<sup>2</sup>/24h for a coating having a coating weight of 20 g/m<sup>2</sup>. The water vapor transmission rate is measured at 90% relative humidity and 38 °C temperature according to the method ASTM E96.